

(54) SOFT METAL CONDUCTOR AND METHOD OF MAKING

(75) Inventor: Rajiv Vasant Joshi, Yorktown Heights, NY (US)

(73) Assignee: International Business Machines Corporation, Armonk, NY (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: 09/112,885

(22) Filed: Jul. 9, 1998

Related U.S. Application Data

(63) Continuation-in-part of application No. 08/367,565, filed on Jan. 3, 1995.

(51) Int. Cl.⁷ H01L 23/48; H01L 23/52; H01L 29/40

(52) U.S. Cl. 257/750; 257/752; 257/758; 257/767

(58) Field of Search 257/750-752, 257/758, 759, 762-765, 767, 771

(56) References Cited

U.S. PATENT DOCUMENTS

5,084,412 A *	1/1992	Nakasaki	438/656
5,143,820 A	9/1992	Kotecha et al.	430/314
5,173,442 A	12/1992	Carey	216/18
5,262,354 A *	11/1993	Cote et al.	216/18
5,266,446 A	11/1993	Chang et al.	430/314
5,281,854 A *	1/1994	Wong	257/740
5,300,813 A	4/1994	Joshi et al.	257/752
5,312,509 A	5/1994	Eschbach	156/345

(List continued on next page.)

OTHER PUBLICATIONS

Y. Arita et al "CVD Copper Metallurgy for ULSI Interconnections" IEDM 90-93. pp. 3.1.1-3.1.4 (IEEE).

W.J. Cote et al. "Electroless Plating for Low-Cost High-Leverage Wiring" IBM Technical Disclosure Bulletin V32/#3A 8/89 pp. 344-345.

IBM Patent Application S.N. 08/768,107 filed Dec. 16, 1996 "Electroplated Interconnection Structures on Integrated Circuit Chips".

Primary Examiner—Carl Whitehead, Jr.

Assistant Examiner—Jamie L. Brophy

(74) Attorney, Agent, or Firm—Robert M. Trepp; Randy W. Tung

(57) ABSTRACT

A soft metal conductor for use in a semiconductor device which has an uppermost layer consisting of grains having grain sizes sufficiently large so as to provide a substantially scratch-free surface upon polishing in a subsequent polishing step. The invention also provides a method for making a soft metal conductor that has a substantially scratch-free surface upon polishing by a multi-step deposition process, i.e., first sputtering at a higher temperature and then sputtering at a lower temperature and followed by another high temperature sputtering process. The invention further discloses a method for forming a substantially scratch-free surface on a soft metal conductor by first depositing a soft metal layer at a low deposition temperature and then annealing the soft metal layer at a higher temperature to increase the grain size of the metal. The invention also discloses a dual-step deposition method for making a soft metal conductor for use in an electronic device by first depositing a first layer of metal by a physical vapor deposition technique to a first thickness, and then depositing a second layer of metal on top of the first layer of metal to a second thickness larger than the first thickness by a method of chemical vapor deposition, electroplating or electroless plating. The first deposition process may further be conducted by a chemical vapor deposition technique, with the second deposition process conducted by a physical vapor deposition technique.

16 Claims, 4 Drawing Sheets

